

**ArChine Refritech PAO 22**

## Polyalphaolefin refrigeration lubricant

**Product Description**

ArChine Refritech PAO 22 is a high quality synthetic polyalphaolefin (PAO) refrigeration lubricant. It is specially formulated for severe service under conditions that are beyond the capabilities of conventional mineral oils. In addition, ArChine Refritech PAO 22 improves the performance and efficiency of standard refrigeration systems to conventional mineral oils, and compatibility with mineral oils and equipment designed for use with mineral oils.

ArChine Refritech PAO 22 has very low pour point, zero wax content, a high natural viscosity index and high thermal stability. It also offers high chemical stability, a low volatility and a high film strength. Due to these properties, ArChine Refritech PAO 22 provides a long service life.

**Features**

- Excellent coolant properties
- Carbon and varnish control to help reduce deposits
- Good anti-wear properties and corrosion protection
- Controls rust for enhanced component protection
- Extended oil change intervals, reducing servicing costs to a minimum
- Increased oxidation protection and superior thermal stability

**Application**

ArChine Refritech PAO 22 is recommended for flooded screw compressors which are operated with ammonia(R717) or CO<sub>2</sub>(R744). This product can also be used with natural hydrocarbon refrigerants like propane(R290), propylene(R1270) or butane(R600).

**Typical Properties\***

ArChine Refritech PAO 22	Standard Specification
--------------------------	------------------------

**Distributor Wanted**

Shanghai PingYiao Trading CO., Ltd.

Address: A1207, Yin Hai Building, No.250, Caoxi Road, Xuhui District, Shanghai 200235 P.R.China

Telephone helpline: (86)15900706965

Website: [www.pingyiao.com](http://www.pingyiao.com)

Tel: 86-21-64705533

Fax: 86-21-64705533-209

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)

# ARCHINE

Shanghai PingYiao Trading CO., Ltd.

Apperance	Light yellow transparent liquid
Density@20°C, g/cm <sup>3</sup>	0.823
Viscosity@40°C, mm <sup>2</sup> /s	21.5
Viscosity@100°C, mm <sup>2</sup> /s	4.48
Viscosity Index	122
Flash Point (open cup, °C)	202
Fire Point, °C	216
Pour Point, °C	-63
Foaming 24°C	10/0
Copper corrosion, 100°C/3hr,grade	1

\*Typical data shall not be used as product specifications.

## Distributor Wanted

Shanghai PingYiao Trading CO., Ltd.

Tel: 86-21-64705533

Adress: A1207, Yin Hai Building, No.250, Caoxi Road, Xuhui District, Shanghai  
200235 P.R.China

Telephone helpline: (86)15900706965

Fax: 86-21-64705533-209

Website: [www.pingyiao.com](http://www.pingyiao.com)

E-mail: [info@pingyiao.com](mailto:info@pingyiao.com)